



### SPC Technical Data

SPC FLOORING ( PONDEROSA, LIFE'S A BEACH, EXOTIC DELIGHTS, URBAN TRENDS )	
USE	RESIDENTIAL AND COMMERCIAL
WATERPROOF	100% WATERPROOF
MATERIAL	PVC, VINYL, UV URETHANE COATED WEAR LAYER
PLANK THICKNESS	4 mm PLANK OR 5.5 MM WITH ATTACHED PAD
WEAR LAYER	20 MIL (0.5mm) OR 12 MIL (0.3 mm)
BEVELS	4 SIDED PAINTED BEVELS
EMBOSSING	HOT PRESSED WITH REGISTERED EMBOSSING
LOCKING SYSTEM	UNILIN TRADEMARKED LOCKING SYSTEM
INSTALLATION	FLOATING
STRUCTURAL WARRANTY	LIMITED LIFETIME STRUCTURAL
FINISH WARRANTY	RESIDENTIAL: 25 YEARS COMMERCIAL: 8 YEARS

### ASTM TEST RESULTS

TEST	RESULTS	REQUIREMENTS
IIC RATINGS/ STC RATING	IIC RATING- 69 WITH ATTACHED PAD	STC RATING- 65 WITH ATTACHED PAD
FORMALDEHYDE EMISSION	PASS	DETECTION LIMIT=0.02 ppm
PHTHALATE CONTENT TEST	NOT DETECTED	PHTHALATE FREE
HEAVY METALS	NOT DETECTED	< THE DETECTION LIMIT
VINYL PLANK STRENGTH	PASS	EN649:2011
ASTM F2055-17 SIZE TOLERANCE	PASS	TOLERANCE OF 0.4 mm
ASTM F386-17 THICKNESS	PASS	COMMERCIAL, 0.5mm MIN
ASTM F2055-17 SQUARENESS	PASS	< 0.25mm
ASTM F1914-17 RESIDUAL INDENTATION	PASS	AVERAGE < 8%
		MAX < 10%
ASTM F2199 DIMENSIONAL STABILITY	PASS	< 0.51mm (0.17%)
ASTM F925-13 RESISTANCE TO CHEMICALS	PASS	NO MORE THAN SLIGHT CHANGE IN
		SURFACE DULLING, OR STAINING
ASTM F1515-15 RESISTANCE TO LIGHT	PASS	$\Delta E^*$ SHALL NOT BE GREATER THAN 8.0
		AFTER 300h EXPOSURE
ASTM F1514-03 RESISTANCE TO HEAT	PASS	$\Delta E^*$ SHALL NOT BE GREATER THAN
		8.0 AFTER 7 DAYS EXPOSURE TO 158°F
ASTM F1037	PASS	EN660-2:2003 AND EN649:2011

#### IMPORTANT NOTICE

Vinyl flooring is sensitive to extreme heat and direct sunlight. To prevent excessive expansion, avoid exposure to direct sunlight for prolonged periods of time. During peak sunlight hours, use drapes or blinds to minimize exposure.